



Bitumen Grade: PG 64-10

Description and Applications:

PG system is a method of measuring asphalt binder performance; In a Super-pave grading system, binders are classified according to their performance in extreme hot and cold temperatures and called Performance Grade Bitumen. The main purpose of grading and selecting asphalt binder using the Performance Grade system is to ensure that the binder has the appropriate properties for environmental conditions in the field. Performance Grade asphalt binders are selected to meet expected climatic conditions as well as traffic speed and volume adjustments. Therefore, the Performance Grade system uses a common set of tests to measure the physical properties of the binder that can be directly related to the field performance of the pavement at its service temperatures by engineering principles.

Characteristics and Specifications:

Based on ASTM D6373 Bitumen.

Health and Safety:

Detailed health and safety information for this product is provided in the Material Safety Data Sheet (MSDS), available upon request.

No	Property	Test Standard	Acceptable Range
Original Binder			
1	Rotational Viscosity, 135 °C (spindle 21, 20rpm)	AASHTO T316	≤3 Pa.s
2	Flash Point, °C	AASHTO T48	≥230 °C
3	DSR, 64 °C (shear strain 12%, 10.0 rad/s)	AASHTO T315	$G^*/\sin\delta \geq 1.0$ KPa
After RTFO Test			
4	Mass Change, 163 °C	AASHTO T240	± 1.0 % Max
5	DSR, 64 °C (shear strain 12%, 10.0 rad/s)	AASHTO T315	$G^*/\sin\delta \geq 2.2$ KPa
After PAV Test			
6	Pressure aging vessel (PAV) aging temperature. °C	AASHTO R 28	100
7	DSR, 31°C (shear strain 1%, 10.0 rad/s)	AASHTO T315	$G^* \cdot \sin\delta \leq 5000$ KPa
8	BBR, 0°C	AASHTO T313	$S \leq 300$ MPa $m \geq 0.3$



Tel: +98 21 72065000



Web: www.bhpb bitumen.com



Email: Info@bhpb bitumen.com



Add: No.11, Golkhane St, Nelson Mandela Blvd, Tehran, Iran