



Bitumen Grade: VG 40

Row No.	Type Test	Standard Range		Test Method	
		Min	Max	INSO	ASTM
1	Specific Gravity at 25°C	-	-	3872	D70
2	Penetration at 25°C (0.1mm)	35	-	2950	D5
3	Softening point (°C)	50	-	3868	D36
4	Flash point, Cleveland Open Cup (°C)	230	-	198	D92
5	Solubility in TCE (wt%)	99	-	2953	D2042
6	Kinematic viscosity at 135°C(Cst)	300	-	12855	D2170
7	Dynamic viscosity at 60 °C (poise)	3200	4800	12851	D2171
8	Penetration index	-1.5	1	EN12607-1	-
9	Spot test	-	-	-	-
10	Solvent (Naphtha)	Negative	Negative	2949	AASHTO102
11	Solvent (Xalene-Naphtha)	Negative	Negative	2949	AASHTO102
12	Solvent (Xalene-Heptane)	Negative	Negative	2949	AASHTO102



Tel: +98 21 72065000



Web: www.bhpbbitumen.com



Email: Info@bhpbbitumen.com



Add: No.11, Golkhane St, Nelson Mandela Blvd, Tehran, Iran