

Bitumen Hormoz Pars

Specification



Bitumen Grade: 200-300

Description and Applications:

Penetration Grade Bitumen is mainly used in road surfacing and some industrial applications. We supply penetration Grade Bitumen which is petroleum based and manufactured from Vacuum Bottom (VB) feedstock. Penetration Grade Bitumen is specified by the penetration and softening point test. Bitumen with lower penetration grade is used in the regions with warm climate while higher penetration grade is used in colder weather.

Characteristics and Specifications:

Based on ASTM D946 Bitumen

Health and Safety:

Detailed health and safety information for this product is provided in the Material Safety Data Sheet (MSDS), available upon request.

Bitumen Grade: 200-300					
Specification					
Row No.	Type Test	Standard Range		Test Method	
		Min	Max	INSO	ASTM
1	Specific Gravity at 25°C	1.01	1.06	3872	D70
2	Penetration at 25°C (0.1mm)	200	300	2950	D5
3	Softening point (°C)	32	-	3868	D36
4	Flash point, Cleveland Open Cup (°C)	175	-	198	D92
5	Ductility at 25°C 5cm/min (cm)	100	-	3866	D113
6	Solubility in TCE (wt%)	99	-	2953	D2042
7	Spot test	Negative	Negative	2949	AASH T0102
8	Change in mass, Wt% (Thin Film oven test, 163°C, 3.2mm, for 5hrs)	-	1.5	2957	D1754
9	Retained Penetration, % (Thin Film oven test, 163°C, 3.2mm, for 5hrs)	37	-	2950-2957	D5-1754
<i>Other Description:</i>					

Bitumen Hormoz Pars

Specification



Bitumen Grade: 60-70

Description and Applications:

Penetration Grade Bitumen is mainly used in road surfacing and some industrial applications. We supply penetration Grade Bitumen which is petroleum based and manufactured from Vacuum Bottom (VB) feedstock. Penetration Grade Bitumen is specified by the penetration and softening point test. Bitumen with lower penetration grade is used in the regions with warm climate while higher penetration grade is used in colder weather.

Characteristics and Specifications:

Based on ASTM D946 Bitumen

Health and Safety:

Detailed health and safety information for this product is provided in the Material Safety Data Sheet (MSDS), available upon request.

Bitumen Grade: 60-70					
<i>specification</i>					
Row No.	Type Test	Standard Range		Test Method	
		Min	Max	INSO	ASTM
1	Specific Gravity at 25°C	1.01	1.06	3872	D70
2	Penetration at 25°C (0.1mm)	60	70	2950	D5
3	Softening point (°C)	46	54	3868	D36
4	Flash point, Cleveland Open Cup (°C)	230	-	198	D92
5	Ductility at 25°C 5cm/min (cm)	100	-	3866	D113
6	Solubility in TCE (wt%)	99	-	2953	D2042
7	Penetration index	-1.5	0.7	EN12607-1	-
8	Spot test	Negative	Negative	2949	AASH TO102
9	Loss on Heating	-	0.2	-	D6
10	Drop in Penetration After Heating (%)	-	20	-	D5&6
<i>Other Description:</i>					

Bitumen Hormoz Pars

Specification



Bitumen Grade: 80-100

Description and Applications:

Penetration Grade Bitumen is mainly used in road surfacing and some industrial applications. We supply penetration Grade Bitumen which is petroleum based and manufactured from Vacuum Bottom (VB) feedstock. Penetration Grade Bitumen is specified by the penetration and softening point test. Bitumen with lower penetration grade is used in the regions with warm climate while higher penetration grade is used in colder weather.

Characteristics and Specifications:

Based on ASTM D946 Bitumen

Health and Safety:

Detailed health and safety information for this product is provided in the Material Safety Data Sheet (MSDS), available upon request.

Bitumen Grade: 80-100					
Specification					
Row No.	Type Test	Standard Range		Test Method	
		Min	Max	INSO	ASTM
1	Specific Gravity at 25°C	1.01	1.06	3872	D70
2	Penetration at 25°C (0.1mm)	80	100	2950	D5
3	Softening point (°C)	42	-	3868	D36
4	Flash point, Cleveland Open Cup (°C)	230	-	198	D92
5	Ductility at 25°C 5cm/min (cm)	100	-	3866	D113
6	Solubility in TCE (wt%)	99	-	2953	D2042
7	Penetration index	-1.5	0.7	EN12607-1	-
8	Spot test	Negative	Negative	2949	AASH TO102
9	Loss on heating 163(°C) wt%	-	0.5	-	D6
10	Drop in Penetration after Heating %	-	20	-	D5&6
<i>Other Description:</i>					

Bitumen Hormoz Pars

Specification



Bitumen Grade: 85-100

Description and Applications:

Penetration Grade Bitumen is mainly used in road surfacing and some industrial applications. We supply penetration Grade Bitumen which is petroleum based and manufactured from Vacuum Bottom (VB) feedstock. Penetration Grade Bitumen is specified by the penetration and softening point test. Bitumen with lower penetration grade is used in the regions with warm climate while higher penetration grade is used in colder weather.

Characteristics and Specifications:

Based on ASTM D946 Bitumen

Health and Safety:

Detailed health and safety information for this product is provided in the Material Safety Data Sheet (MSDS), available upon request.

Bitumen Grade: 85-100					
Specification					
Row No.	Type Test	Standard Range		Test Method	
		Min	Max	INSO	ASTM
1	Specific Gravity at 25°C	1.01	1.06	3872	D70
2	Penetration at 25°C (0.1mm)	85	100	2950	D5
3	Softening point (°C)	42	-	3868	D36
4	Flash point, Cleveland Open Cup (°C)	230	-	198	D92
5	Ductility at 25°C 5cm/min (cm)	100	-	3866	D113
6	Solubility in TCE (wt%)	99	-	2953	D2042
7	Penetration index	-1.5	0.7	EN12607-1	-
8	Spot test	Negative	Negative	2949	AASH TO102
9	Loss on heating 163(°C) wt%	-	0.5	-	D6
10	Drop in Penetration after Heating %	-	20	-	D5&6
<i>Other Description:</i>					